



TECHNICAL INFORMATION

2114 DIARYLIDE YELLOW 14

C. I. PIGMENT YELLOW 14 C. I. NO. 21095

DESCRIPTION

A semi-opaque AAOT Diarylide Yellow offering excellent value. LANSCO 2114 is stronger and slightly greener than 2014.

TYPICAL PHYSICAL PROPERTIES

Bulk Density	11.1 lbs/gal
pH (10% Aqueous Slurry)	5.0 - 7.5
Moisture Content %	< 2.00
Water Soluble Salts %	< 2.00
Oil Absorption	40 wt/100 wt

BLEED CHARACTERISTICS

Xylene	Sl. Soluble
Ethanol	Trace
Mineral Spirit	None
Lacquer Solvents	Trace
Water	None

LIGHTFASTNESS

Full Shade:	Fair
Tint:	Poor

CHEMICAL RESISTANCE

Acid:	Excellent
Alkali:	Excellent

HEAT STABILITY (Plastics)

390° F 200° C

HEAT STABILITY (Coatings)

345° F 174° C

SUGGESTED USES

2114 AAOT Yellow is suggested mainly for water based inks.

LANSCO COLORS

305 WEST GRAND AVE., MONTVALE, NJ 07645 • 201-307-5995 • FAX 201-307-5855

The information contained herein is true and accurate to the best of our knowledge, but is provided without warranty or guarantee. Since the conditions of use are beyond our control, Landers-Segal Color Co., Inc. assumes no legal responsibility for use or reliance upon the information contained herein. Landers-Segal Color Co. strongly recommends careful screening/testing before using its products in production.