



TECHNICAL INFORMATION

2162 AZO YELLOW 62

C. I. PIGMENT YELLOW 62

C. I. NO. 13940

DESCRIPTION

A mono azo yellow calcium precipitated pigment with good lightfastness, chemical resistance and heat stability. Similar to medium chrome yellow in masstone and light chrome yellow in tint.

TYPICAL PHYSICAL PROPERTIES

Bulk Density	1.66 lbs/gal
pH (10% Aqueous Slurry)	6.0-7.0
Moisture Content %	< 2.00
Water Soluble Salts %	< 2.00
Oil Absorption	48.0 wt/100 wt

BLEED CHARACTERISTICS

Xylol	N/A
Ethanol	N/A
Mineral Spirit	N/A
Lacquer Solvents	N/A
Water	None

LIGHTFASTNESS

Full Shade:	Fair
Tint:	Fair

CHEMICAL RESISTANCE

Acid:	Good
Alkali:	Good

HEAT STABILITY (Plastics)

500° F

HEAT STABILITY (Coatings)

N/A

SUGGESTED USES

2162 can be used in blow molded and injection molded polyolefins as a lead-free/cadmium free alternative. It can also be used in rigid and plasticized PVC.

LANSCO COLORS

305 WEST GRAND AVE., MONTVALE, NJ 07645 • 201-307-5995 • FAX 201-307-5855

The information contained herein is true and accurate to the best of our knowledge, but is provided without warranty or guarantee. Since the conditions of use are beyond our control, Landers-Segal Color Co., Inc. assumes no legal responsibility for use or reliance upon the information contained herein. Landers-Segal Color Co. strongly recommends careful screening/testing before using its products in production.