



# TECHNICAL INFORMATION

## 2217 DIARYLIDE YELLOW 17

C. I. PIGMENT YELLOW 17 C. I. NO. 21105

### DESCRIPTION

An excellent quality clean and strong green shade AAOA Diarylide Yellow. Tinting strength is superior to inorganic counterparts. An excellent value.

### TYPICAL PHYSICAL PROPERTIES

Bulk Density	11.9 lbs/gal
pH (10% Aqueous Slurry)	5.0 - 7.5
Moisture Content %	< 2.0
Water Soluble Salts %	< 2.0
Oil Absorption	55 wt/100 wt

### BLEED CHARACTERISTICS

Xylene	Sl. Soluble
Ethanol	Trace
Mineral Spirit	None
Lacquer Solvents	Trace
Water	None

### LIGHTFASTNESS

Full Shade:	Fair
Tint:	Poor

### CHEMICAL RESISTANCE

Acid:	Excellent
Alkali:	Excellent

### HEAT STABILITY (Plastics)

390° F 200° C

### HEAT STABILITY (Coatings)

345° F 174° C

### SUGGESTED USES

2217 AAOA Yellow is suggested mainly for aqueous inks and textile printing. Also, selected use in plastics, interior coatings and rubber.

### LANSCO COLORS

305 WEST GRAND AVE., MONTVALE, NJ 07645 • 201-307-5995 • FAX 201-307-5855

The information contained herein is true and accurate to the best of our knowledge, but is provided without warranty or guarantee. Since the conditions of use are beyond our control, Landers-Segal Color Co., Inc. assumes no legal responsibility for use or reliance upon the information contained herein. Landers-Segal Color Co. strongly recommends careful screening/testing before using its products in production.