



TECHNICAL INFORMATION

LANSCO #243-XF ZINC CHROMATE

An easy dispersing, chromate-based product with excellent outdoor durability for anticorrosive coatings.

TYPICAL ANALYSIS

Zinc, calc. as ZnO.....	35 - 40%
Chromium	min 42%
Chlorides.....	max 0.1%
Sulphates	max 0.1%
Residue on 325 mesh screen	max 0.3%
Specific gravity.....	3.5
Oil absorption value	25 g/100g
pH of aqueous suspension	about 7.2

LANSCO COLORS

305 WEST GRAND AVE., MONTVALE, NJ 07645 • 201-307-5995 • FAX 201-307-5855

The information contained herein is true and accurate to the best of our knowledge, but is provided without warranty or guarantee. Since the conditions of use are beyond our control, Landers-Segal Color Co., Inc. assumes no legal responsibility for use or reliance upon the information contained herein. Landers-Segal Color Co. strongly recommends careful screening/testing before using its products in production.