



# TECHNICAL INFORMATION

## 2874 HANSA YELLOW 74

C. I. PIGMENT YELLOW 74 C. I. NO. 11741

### DESCRIPTION

2874 is a green shade Hansa Yellow mainly used in aqueous coatings and inks. Yellow 74 has better lightfastness than Diarylide Yellow.

### TYPICAL PHYSICAL PROPERTIES

Bulk Density	11.9 lbs/gal
pH (10% Aqueous Slurry)	6.0 - 7.0
Moisture Content %	< 2.0
Water Soluble Salts %	< 2.0
Oil Absorption	36 wt/100 wt

### BLEED CHARACTERISTICS

Xylene	Soluble
Ethanol	Sl. Soluble
Mineral Spirit	Trace
Lacquer Solvents	Soluble
Water	None

### LIGHTFASTNESS

Full Shade: Good  
Tint: Fair

### CHEMICAL RESISTANCE

Acid: Excellent  
Alkali: Excellent

### HEAT STABILITY (Coatings)

250° F 120° C

### SUGGESTED USES

2874 Hansa Yellow 74 is used in trade paints as an interior yellow. It is also used in water flexo inks where lightfastness that is better than Diarylide Yellow is required. It is not recommended for plastics.

### LANSCO COLORS

305 WEST GRAND AVE., MONTVALE, NJ 07645 • 201-307-5995 • FAX 201-307-5855

The information contained herein is true and accurate to the best of our knowledge, but is provided without warranty or guarantee. Since the conditions of use are beyond our control, Landers-Segal Color Co., Inc. assumes no legal responsibility for use or reliance upon the information contained herein. Landers-Segal Color Co. strongly recommends careful screening/testing before using its products in production.