



TECHNICAL INFORMATION

2883 OPAQUE DIARYLIDE YELLOW 83

C. I. PIGMENT YELLOW 83 C. I. NO. 21108

DESCRIPTION

2883 is a medium shade Diarylide Yellow offering good opacity, lightfastness, and tinting strength compared to other Diarylide Yellows.

TYPICAL PHYSICAL PROPERTIES

Bulk Density	12.1 lbs/gal
pH (10% Aqueous Slurry)	5.5 - 6.5
Moisture Content %	< 1.0
Water Soluble Salts %	< 1.0
Oil Absorption	80 wt/100 wt

BLEED CHARACTERISTICS

Xylene	Sl. Soluble
Ethanol	Trace
Mineral Spirit	None
Lacquer Solvents	Sl. Soluble
Water	None

LIGHTFASTNESS

Full Shade:	V Good
Tint:	Fair

CHEMICAL RESISTANCE

Acid:	Excellent
Alkali:	Excellent

HEAT STABILITY (Plastics)

390° F 200° C

HEAT STABILITY (Coatings)

375° F 190° C

SUGGESTED USES

2883 Diarylide Yellow 83 is recommended for use in coatings, plastics and inks.

LANSCO COLORS

305 WEST GRAND AVE., MONTVALE, NJ 07645 • 201-307-5995 • FAX 201-307-5855

The information contained herein is true and accurate to the best of our knowledge, but is provided without warranty or guarantee. Since the conditions of use are beyond our control, Landers-Segal Color Co., Inc. assumes no legal responsibility for use or reliance upon the information contained herein. Landers-Segal Color Co. strongly recommends careful screening/testing before using its products in production.