



TECHNICAL INFORMATION

TECHNICAL INFORMATION

LANSCO 462 CARBON BLACK

Jetness Index	99
Surface Area M2/gm	25
Particle Diameter (NM)	75
DPB Absorption (cc/100 grams)	72
Tinting Strength Index	58
Volatile Content %	0.5
Density LBS/Cu. Ft.	18

Typical Values

LANSCO COLORS

305 WEST GRAND AVE., MONTVALE, NJ 07645 • 201-307-5995 • FAX 201-307-5855

The information contained herein is true and accurate to the best of our knowledge, but is provided without warranty or guarantee. Since the conditions of use are beyond our control, Landers-Segal Color Co., Inc. assumes no legal responsibility for use or reliance upon the information contained herein. Landers-Segal Color Co. strongly recommends careful screening/testing before using its products in production.