



TECHNICAL INFORMATION

LANSCO 463 CARBON BLACK

Particle Diameter (nM)	45
Oil Absorption (cc/100 grams)	137
Density (lbs/ft ³)	9
ASTM Tinting Strength (%)	60
Nitrogen Surface Area N ₂ SA (m ² /gram)	42

Typical Values

LANSCO COLORS

305 WEST GRAND AVE., MONTVALE, NJ 07645 • 201-307-5995 • FAX 201-307-5855

The information contained herein is true and accurate to the best of our knowledge, but is provided without warranty or guarantee. Since the conditions of use are beyond our control, Landers-Segal Color Co., Inc. assumes no legal responsibility for use or reliance upon the information contained herein. Landers-Segal Color Co. strongly recommends careful screening/testing before using its products in production.