



TECHNICAL INFORMATION

LANSCO 7058

ALUMINUM PASTE CB-200 S-65

Non-Volatile Content	65%
Mineral Spirit	35%
Leafing Value %	> 65
Leafing Stability	Excellent
d50 ,um (Malvern)	11 - 17
Surface Coverage (butanol) cm ² /g	27.000 - 32.000
Water Content %	< 0,15
Density g/cm ³	1,0 - 1,5
Matter Soluble in Organic Solvent max %	3,0
Residue on 325 mesh = 44 ,um %	< 0,1

LANSCO COLORS

305 WEST GRAND AVE., MONTVALE, NJ 07645 201-307-5995 • FAX 201-307-5855

The information contained herein is true and accurate to the best of our knowledge, but is provided without warranty or guarantee. Since the conditions of use are beyond our control, Landers-Segal Color Co., Inc. assumes no legal responsibility for use or reliance upon the information contained herein. Landers-Segal Color Co. strongly recommends careful screening/testing before using its products in production.