



TECHNICAL DATA SHEET

PG-631 PHTHALO GREEN 7

C. I. PIGMENT GREEN 7

C. I. NO. 74260

DESCRIPTION

PG-631 is our bluest shade phthalocyanine offering excellent tinting strength.

Typical Physical Properties

Specific gravity	1.80 – 2.10
pH (10% Aqueous Slurry)	~ 6.0 – 8.0
Moisture Content	< 2.0%
Oil Absorption	~ 20 – 25

Bleed Characteristics

Xylene	5
Ethanol	5
Methyl Ethyl Ketone	5
Mineral Spirits	5
Water	5

Lightfastness

Full Shade	8
Tint	8

Chemical Resistance

Acid	5
Alkali	5

Heat Stability

Inks	350°F
Coatings	390°F

SUGGESTED USES

Primarily recommended for UV Ink Systems. Also suitable for water flexo inks, metal deco, solvent packaging ink systems and offset inks. May also be suitable for coatings and plastics applications.

1/2007

LANSCO COLORS

305 WEST GRAND AVE., MONTVALE, NJ 07645 • PHONE 201-307-5995 • FAX 201-307-5855
191 SECOND AVE., WARWICK, RI 02888 • PHONE 401-461-4100 • FAX 401-785-9323
5866 S. STAPLES ST., SUITE 333, CORPUS CHRISTI, TX 78413 • PHONE 361-985-9696 • FAX 361-985-6006

LIMITED WARRANTY: Seller warrants that its products are free from manufacturing defects. The Seller makes no other warranty beyond that contained in this writing. DISCLAIMER OF OTHER WARRANTIES: NO OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, SHALL APPLY. DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY THE SELLER: The information contained herein is true and accurate to the best of our knowledge, but is provided without warranty or guarantee. Since the conditions of use are beyond our control, Seller disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. Seller strongly recommends careful screening/testing before using its products in production. TIME LIMIT FOR BRINGING SUIT: All suits must be commenced within one-year from the date on which the product at issue is delivered to Buyer.