



TECHNICAL DATA SHEET

PR-251 2B RED 48:3

C. I. PIGMENT RED 48:3

C. I. NO. 15865:3

DESCRIPTION

Bluer shade strontium salt, noted for its excellent brightness and tint strength. An alternative to Barium Lithol with good wax bleed resistance.

Typical Physical Properties

Specific gravity	~ 1.65
pH (10% Aqueous Slurry)	7.0 – 8.5
Moisture Content	< 2.0%
Oil Absorption	40 – 50

Bleed Characteristics

Ethyl Acetate	4 – 5
Ethanol	4
Isopropanol	4 – 5
Mineral Spirits	4 – 5
Water	5

Lightfastness (1–8 Rating) 8 indicates no change

Full Shade	3
Tint	3

Chemical Resistance

Acid	3
Alkali	4 - 5

Heat Stability

Plastics	390 – 400°F
----------	-------------

SUGGESTED USES

Suitable for low temperature plastics, interior air dry coatings. Also recommended for water based inks.

02/07

LANSCO COLORS

305 WEST GRAND AVE., MONTVALE, NJ 07645 • PHONE 201-307-5995 • FAX 201-307-5855
191 SECOND AVE., WARWICK, RI 02888 • PHONE 401-461-4100 • FAX 401-785-9323
5866 S. STAPLES ST., SUITE 333, CORPUS CHRISTI, TX 78413 • PHONE 361-985-9696 • FAX 361-985-6006

LIMITED WARRANTY: Seller warrants that its products are free from manufacturing defects. The Seller makes no other warranty beyond that contained in this writing. DISCLAIMER OF OTHER WARRANTIES: NO OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, SHALL APPLY. DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY THE SELLER: The information contained herein is true and accurate to the best of our knowledge, but is provided without warranty or guarantee. Since the conditions of use are beyond our control, Seller disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. Seller strongly recommends careful screening/testing before using its products in production. TIME LIMIT FOR BRINGING SUIT: All suits must be commenced within one-year from the date on which the product at issue is delivered to Buyer.