



2151 Benzimidazolone Yellow 151

Description: 2151 is a green shade yellow pigment with excellent light and weather fastness, especially in deep shades. 2151 has high opacity and good flow properties in all types of coatings.

Chemical Type	Benzimidazolone Yellow	Constitution No.	13980
Color Index	Pigment Yellow 151	CAS No.	31837-42-0

Resistance Properties

MEK	4 - 5	Ethanol	4 - 5
Water	5	Ethyl Acetate	5
Mineral Spirits	5	Acid	5
Xylene	4 - 5	Alkali	3

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Product Characteristics

Migration (1-5)		Lightfastness (1-8): Masstone	8
Heat Stability (°C/°F)	199°C (Paint) 260°C (HDPE)	Lightfastness (1-8): Tint 1:10	7 - 8
Warpage Rating (1-3) * Plastic Only		Weatherfastness (1-5): Masstone	
Overpaint Resistance * Paints Only		Weatherfastness (1-5): Tint 1:10	

Warpage: 1 = minimal, 2 = some, 3 = severe Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=Very Good, 8=Excellent

Physical Properties

Particle Size (µm)		pH	5.0 - 7.5
Specific Surface Area (m²/g)		Specific Gravity	1.5
Oil Absorption (g/100g)	35-45	Bulk Density (kg/L)	
Moisture Content (%)	≤ 1.0%	Bulk Volume (L/kg)	

Applications

Plastics		Coatings		Inks		Other	
PVC	<input type="checkbox"/>	Decorative	<input type="checkbox"/>	Water Flexo	<input type="checkbox"/>	Paper	
PE	<input type="checkbox"/>	Automotive/Aerospace	<input checked="" type="checkbox"/>	Solvent Flexo	<input type="checkbox"/>	Rubber	
PP	<input type="checkbox"/>	Industrial	<input checked="" type="checkbox"/>	InkJet	<input checked="" type="checkbox"/>	Finger Paints	
PS	<input type="checkbox"/>	Powder	<input checked="" type="checkbox"/>	UV	<input type="checkbox"/>	Seed Coatings	
PET	<input type="checkbox"/>			Offset	<input type="checkbox"/>		
Fiber	<input type="checkbox"/>						

Not Frequently Used Limited Recommended

Comments:

DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL: The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production.