



# 2194 Benzimidazolone Yellow 194

**Description:** 2194 is a bright, green shade yellow with very good light and weather fastness, especially in deep shades. This product has relatively high opacity, good flow properties and bleed characteristics.

<b>Chemical Type</b>	Benzimidazolone Yellow	<b>Constitution No.</b>	82119-12-0
<b>Color Index</b>	Pigment Yellow 194	<b>CAS No.</b>	82199-12-0

## Resistance Properties

<b>MEK</b>	4	<b>Ethanol</b>	4
<b>Water</b>	5	<b>Ethyl Acetate</b>	4
<b>Mineral Spirits</b>	4 - 5	<b>Acid</b>	5
<b>Xylene</b>	3	<b>Alkali</b>	5

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

## Product Characteristics

<b>Migration (1-5)</b>		<b>Lightfastness (1-8): Masstone</b>	7-8
<b>Heat Stability (°C/°F)</b>	199°C (Paints)	<b>Lightfastness (1-8): Tint 1:10</b>	7
<b>Warpage Rating (1-3) * Plastic Only</b>		<b>Weatherfastness (1-5): Masstone</b>	
<b>Overpaint Resistance * Paints Only</b>		<b>Weatherfastness (1-5): Tint 1:10</b>	

Warpage: 1 = minimal, 2 = some, 3 = severe    Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent    Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=Very Good, 8=Excellent

## Physical Properties

<b>Particle Size (µm)</b>		<b>pH</b>	5.5-7.5
<b>Specific Surface Area (m<sup>2</sup>/g)</b>		<b>Specific Gravity</b>	1.5
<b>Oil Absorption (g/100g)</b>	40-45	<b>Bulk Density (kg/L)</b>	
<b>Moisture Content (%)</b>	≤ 1.0%	<b>Bulk Volume (L/kg)</b>	

## Applications

Plastics		Coatings		Inks		Other	
PVC	■	Decorative	□	Water Flexo	■	Paper	
PE	■	Automotive/Aerospace	□	Solvent Flexo	■	Rubber	
PP	□	Industrial	■	InkJet	■	Finger Paints	
PS	□	Powder	■	UV	■	Seed Coatings	
PET	□			Offset	■		
Fiber	□						

□ Not Frequently Used    □ Limited    ■ Recommended

### Comments:

**DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL:** The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production.