



2810M Syn Micronized Yellow Iron Oxide

Lanox Iron Oxide

Description: 2810M has superior dispersibility and hiding with lower oil absorption. 2810M is an offset to the Bayferrox 3910M and is FDA approved (Section 178.3297).

Chemical Type	Syn Micronized Yellow Iron Oxide	Constitution No.	77492
Color Index	Pigment Yellow 42	CAS No.	51274-00-1

Typical Chemical and Physical Properties

Fe Content (Fe₂O₃) - % Min.	86
Volatile Matter (220°F) - % Max.	1.0
pH	4.0 - 7.0
Particle Shape	Acicular
Water Soluble Salts (% Max.)	0.30
Oil Absorption (g/100g)	18 - 28
Sieve Residue (325 mesh) - % Max.	0.05
Tamped Apparent Density (g/cm³)	0.50
Density (g/cm³)	4.10
Heat Stability	171°C (HDPE)
Moisture Content (%)	<1.0
Weatherfastness	5
Lightfastness	8

Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=Very Good, 8=Excellent

Applications

Plastics		Coatings		Inks		Other	
PVC	■	Decorative	■	Water Flexo		Paper	
PE	■	Automotive/Aerospace		Solvent Flexo		Rubber	
PP		Industrial	■	InkJet		Finger Paints	
PS		Powder		UV		Seed Coatings	
PET				Offset			

Fiber

Not Frequently Used Limited Recommended

Comments:

DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL: The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production.