



# 5561 Phthalo Blue 15:0

**Description:** 5561 is an alpha, red shade, crystallizing phthalocyanine blue. 5561 is FDA approved (Section 178.3297)

<b>Chemical Type</b>	Phthalo Blue	<b>Constitution No.</b>	74160
<b>Color Index</b>	Pigment Blue 15:0	<b>CAS No.</b>	147-14-8

## Resistance Properties

<b>MEK</b>	5	<b>Ethanol</b>	5
<b>Water</b>	5	<b>Ethyl Acetate</b>	5
<b>Mineral Spirits</b>	5	<b>Acid</b>	5
<b>Xylene</b>	4	<b>Alkali</b>	5

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

## Product Characteristics

<b>Migration (1-5)</b>		<b>Lightfastness (1-8): Masstone</b>	8
<b>Heat Stability (°C/°F)</b>	180°C (Inks) 199°C (HDPE)	<b>Lightfastness (1-8): Tint 1:10</b>	8
<b>Warpage Rating (1-3) * Plastic Only</b>		<b>Weatherfastness (1-5): Masstone</b>	
<b>Overpaint Resistance * Paints Only</b>		<b>Weatherfastness (1-5): Tint 1:10</b>	

Warpage: 1 = minimal, 2 = some, 3 = severe    Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent    Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=Very Good, 8=Excellent

## Physical Properties

<b>Particle Size (µm)</b>		<b>pH</b>	6.5 - 8.0
<b>Specific Surface Area (m²/g)</b>		<b>Specific Gravity</b>	1.6
<b>Oil Absorption (g/100g)</b>	36	<b>Bulk Density (kg/L)</b>	
<b>Moisture Content (%)</b>	<2.0%	<b>Bulk Volume (L/kg)</b>	

## Applications

Plastics		Coatings		Inks		Other	
PVC	■	Decorative	<input type="checkbox"/>	Water Flexo	■	Paper	
PE	□	Automotive/Aerospace	<input type="checkbox"/>	Solvent Flexo	<input type="checkbox"/>	Rubber	■
PP	<input type="checkbox"/>	Industrial	<input type="checkbox"/>	InkJet	<input type="checkbox"/>	Finger Paints	
PS	<input type="checkbox"/>	Powder	<input type="checkbox"/>	UV	<input type="checkbox"/>	Seed Coatings	
PET	<input type="checkbox"/>			Offset	<input type="checkbox"/>		
Fiber	<input type="checkbox"/>						

Not Frequently Used     Limited     Recommended

### Comments:

**DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL:** The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production.