



5651 Phthalo Blue 15:1

Description: 5651 is an alpha crystal form red shade phthalocyanine blue. 5651 is FDA approved (Section 178.3297)

Chemical Type	Phthalo Blue	Constitution No.	74160
Color Index	Pigment Blue 15:1	CAS No.	147-14-8

Resistance Properties

MEK	5	Ethanol	5
Water	5	Ethyl Acetate	5
Mineral Spirits	5	Acid	5
Xylene	4	Alkali	5

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Product Characteristics

Migration (1-5)		Lightfastness (1-8): Masstone	8
Heat Stability (°C/°F)	200°C (Paints) 280°C (PP)	Lightfastness (1-8): Tint 1:10	8
Warpage Rating (1-3) * Plastic Only		Weatherfastness (1-5): Masstone	
Overpaint Resistance * Paints Only		Weatherfastness (1-5): Tint 1:10	

Warpage: 1 = minimal, 2 = some, 3 = severe Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=Very Good, 8=Excellent

Physical Properties

Particle Size (µm)		pH	5.0 - 8.0
Specific Surface Area (m²/g)		Specific Gravity	1.6
Oil Absorption (g/100g)	28 - 34	Bulk Density (kg/L)	
Moisture Content (%)	<1.0%	Bulk Volume (L/kg)	

Applications

Plastics		Coatings		Inks		Other	
PVC	■	Decorative	■	Water Flexo	■	Paper	
PE	■	Automotive/Aerospace	□	Solvent Flexo	□	Rubber	
PP	■	Industrial	■	InkJet	□	Finger Paints	
PS	□	Powder	■	UV	■	Seed Coatings	
PET	□			Offset	■		
Fiber	□						

□ Not Frequently Used □ Limited ■ Recommended

Comments:

DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL: The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production.