



8130M Syn Micronized Red Iron Oxide

Lanox Iron Oxide

Description: 8130M is a micronized synthetic red iron oxide. 8130M is less yellow than 8110M. 8130M is FDA approved.

Chemical Type	Syn Micronized Red Iron Oxide	Constitution No.	77491
Color Index	Pigment Red 101	CAS No.	1309-37-1

Typical Chemical and Physical Properties

Fe Content (Fe₂O₃) - % Min.	96
Volatile Matter (220°F) - % Max.	0.50
pH	4.5 – 7.5
Particle Shape	Spherical
Water Soluble Salts (% Max.)	0.60
Oil Absorption (g/100g)	28
Sieve Residue (325 mesh) - % Max.	0.008
Tamped Apparent Density (g/cm³)	0.70 – 1.00
Density (g/cm³)	5.0
Heat Stability	504°C (HDPE)
Moisture Content (%)	<1.0
Weatherfastness	5
Lightfastness	8

Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=Very Good, 8=Excellent

Applications

Plastics		Coatings		Inks		Other	
PVC	■	Decorative	■	Water Flexo		Paper	
PE	■	Automotive/Aerospace		Solvent Flexo		Rubber	
PP	■	Industrial	■	InkJet		Finger Paints	
PS	■	Powder	■	UV		Seed Coatings	
PET	■			Offset			

Fiber

Not Frequently Used Limited Recommended

Comments:

DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL: The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production.