



8200 Phthalo Blue 15:2

Description: 8200 is an alpha, red shade, phthalocyanine blue treated to provide crystal stability and flocculation resistance. 8200 is FDA approved (Section 178.3297).

Chemical Type	Phthalo Blue	Constitution No.	74160
Color Index	Pigment Blue 15:2	CAS No.	147-14-8

Resistance Properties

MEK	5	Ethanol	5
Water	5	Ethyl Acetate	5
Mineral Spirits	5	Acid	5
Xylene	5	Alkali	5

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Product Characteristics

Migration (1-5)		Lightfastness (1-8): Masstone	8
Heat Stability (°C/°F)	200°C (Paints) 260°C (PP)	Lightfastness (1-8): Tint 1:10	8
Warpage Rating (1-3) * Plastic Only		Weatherfastness (1-5): Masstone	
Overpaint Resistance * Paints Only	5	Weatherfastness (1-5): Tint 1:10	

Warpage: 1 = minimal, 2 = some, 3 = severe Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=Very Good, 8=Excellent

Physical Properties

Particle Size (µm)		pH	6.0 - 7.0
Specific Surface Area (m²/g)		Specific Gravity	1.6
Oil Absorption (g/100g)	40	Bulk Density (kg/L)	
Moisture Content (%)	≤ 1.0%	Bulk Volume (L/kg)	

Applications

Plastics	Coatings	Inks	Other
PVC <input type="checkbox"/>	Decorative <input checked="" type="checkbox"/>	Water Flexo <input type="checkbox"/>	Paper
PE <input type="checkbox"/>	Automotive/Aerospace <input type="checkbox"/>	Solvent Flexo <input type="checkbox"/>	Rubber
PP <input type="checkbox"/>	Industrial <input checked="" type="checkbox"/>	InkJet <input type="checkbox"/>	Finger Paints
PS <input type="checkbox"/>	Powder <input checked="" type="checkbox"/>	UV <input type="checkbox"/>	Seed Coatings
PET <input type="checkbox"/>		Offset <input type="checkbox"/>	
Fiber <input type="checkbox"/>			

Not Frequently Used Limited Recommended

Comments:

DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL: The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production.