



# 8330 Syn Black Iron Oxide

Lanox Iron Oxide

**Description:** 8330 is a synthetic black iron oxide with outstanding weather resistance.

<b>Chemical Type</b>	Syn Black Iron Oxide	<b>Constitution No.</b>	77499
<b>Color Index</b>	Pigment Black 11	<b>CAS No.</b>	1309-38-2, 1317-61-9, 12227-89-3

## Typical Chemical and Physical Properties

<b>Fe Content (Fe<sub>2</sub>O<sub>3</sub>) - % Min.</b>	90
<b>pH</b>	5.0 – 8.0
<b>Volatile Matter (220°F) - % Max.</b>	2.0
<b>Water Soluble Salts (% Max.)</b>	1.0
<b>Oil Absorption (g/100g)</b>	15 - 25
<b>Sieve Residue (325 mesh) - % Max.</b>	0.4
<b>Density (g/cm<sup>3</sup>)</b>	5.0 – 6.0
<b>Weatherfastness</b>	5
<b>Lightfastness</b>	8

Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent    Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=Very Good, 8=Excellent

## Applications

Plastics	Coatings	Inks	Other
PVC	Decorative <input checked="" type="checkbox"/>	Water Flexo	Paper
PE	Automotive/Aerospace <input checked="" type="checkbox"/>	Solvent Flexo	Rubber
PP	Industrial <input checked="" type="checkbox"/>	InkJet	Finger Paints
PS	Powder <input checked="" type="checkbox"/>	UV	Seed Coatings
PET		Offset	

### Fiber

Not Frequently Used     Limited     Recommended

**Comments:** 8330 is recommended for use in the construction industry for the coloration of concrete.

**DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL:** The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production.