



# 8960 Syn Yellow Iron Oxide

Lanox Iron Oxide

**Description:** 8960 is an orange yellow iron oxide with excellent chemical and weather resistance and excellent opacity.

<b>Chemical Type</b>	Syn Yellow Iron Oxide	<b>Constitution No.</b>	77492
<b>Color Index</b>	Pigment Yellow 42	<b>CAS No.</b>	51274-00-1

## Typical Chemical and Physical Properties

<b>Fe Content (Fe<sub>2</sub>O<sub>3</sub>) - % Min.</b>	88
<b>Volatile Matter (220°F) - % Max.</b>	1.0
<b>pH</b>	4.0 - 7.0
<b>Water Soluble Salts (% Max.)</b>	0.50
<b>Oil Absorption (g/100g)</b>	20 - 30
<b>Sieve Residue (325 mesh) - % Max.</b>	≤0.3
<b>Density (g/cm<sup>3</sup>)</b>	4.10
<b>Weatherfastness</b>	5
<b>Lightfastness</b>	8

Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent    Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=Very Good, 8=Excellent

## Applications

Plastics	Coatings	Inks	Other
PVC <input checked="" type="checkbox"/>	Decorative <input checked="" type="checkbox"/>	Water Flexo	Paper
PE <input checked="" type="checkbox"/>	Automotive/Aerospace	Solvent Flexo	Rubber
PP	Industrial	InkJet	Finger Paints
PS	Powder	UV	Seed Coatings
PET		Offset	

### Fiber

Not Frequently Used     Limited     Recommended

**Comments:** 8960 is recommended for use in the construction industry for the coloration of concrete.

**DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL:** The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production.