



## DCC Orange 5606

**Description:** DCC Orange 5606 is a pre-darken SO2 resistant high performance blue shade moly orange pigment with stir-in properties and is recommended for high-end coating and plastic applications.

<b>Chemical Type</b>	Molybdate Orange	<b>Constitution No.</b>	77605
<b>Color Index</b>	Pigment Red 104	<b>CAS No.</b>	12656-85-8

### Resistance Properties

<b>MEK</b>	5	<b>Ethanol</b>	5
<b>Water</b>	5	<b>Ethyl Acetate</b>	5
<b>Mineral Spirits</b>	5	<b>Acid</b>	2
<b>Xylene</b>	5	<b>Alkali</b>	1

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

### Product Characteristics

<b>Migration (1-5)</b>	5	<b>Lightfastness (1-8): Masstone</b>	8
<b>Heat Stability (°C/°F)</b>	200°C (Paints) 270°C (HDPE)	<b>Lightfastness (1-8): Tint 1:10</b>	8
<b>Warpage Rating (1-3) * Plastic Only</b>		<b>Weatherfastness (1-5): Masstone</b>	5
<b>Overpaint Resistance * Paints Only</b>	5	<b>Weatherfastness (1-5): Tint 1:10</b>	5

Warpage: 1 = minimal, 2 = some, 3 = severe    Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent    Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=Very Good, 8=Excellent

### Physical Properties

<b>Particle Size (µm)</b>		<b>pH</b>	5.5-8.5
<b>Specific Surface Area (m<sup>2</sup>/g)</b>		<b>Specific Gravity</b>	5.3
<b>Oil Absorption (g/100g)</b>	13	<b>Bulk Density (kg/L)</b>	
<b>Moisture Content (%)</b>	<1.0%	<b>Bulk Volume (L/kg)</b>	

### Applications

Plastics		Coatings		Inks		Other	
PVC	■	Decorative	□	Water Flexo	□	Paper	
PE	■	Automotive/Aerospace	■	Solvent Flexo	□	Rubber	
PP	■	Industrial	■	InkJet	□	Finger Paints	
PS	■	Powder	■	UV	□	Seed Coatings	
PET	□			Offset	□		
Fiber	□						

□ Not Frequently Used    ■ Limited    ■ Recommended

**Comments:** Restricted to industrial and professional inks, coatings, plastics and roadmarking (subject to regional legislation) This product must not be used for decorative coatings, children's articles (including toys, paints, jewelry and equipment), consumer products, printing inks for consumer products, food and food packaging, drugs and medical devices, ceramics and glassware, cosmetics and tattoos.

**DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL:** The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production.