



DCC Orange 7036

Description: DCC Orange 7036 is a high performance blue shade orange pigment for use in high-end coatings applications where very good weatherfastness and heat stability are required. DCC Orange 7036 is a very cost effective lead free alternative to molybdate orange.

Chemical Type	Benzimidazolone Orange	Constitution No.	11780
Color Index	Pigment Orange 36	CAS No.	12236-62-3

Resistance Properties

MEK	4	Ethanol	4
Water	5	Ethyl Acetate	4
Mineral Spirits	4	Acid	5
Xylene	4	Alkali	5

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Product Characteristics

Migration (1-5)	5	Lightfastness (1-8): Masstone	8
Heat Stability (°C/°F)	200°C (Paints)	Lightfastness (1-8): Tint 1:10	8
Warpage Rating (1-3) * Plastic Only		Weatherfastness (1-5): Masstone	5
Overpaint Resistance * Paints Only	5	Weatherfastness (1-5): Tint 1:10	4

Warpage: 1 = minimal, 2 = some, 3 = severe Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=Very Good, 8=Excellent

Physical Properties

Particle Size (µm)		pH	5.5-8.5
Specific Surface Area (m²/g)		Specific Gravity	1.6
Oil Absorption (g/100g)	34	Bulk Density (kg/L)	
Moisture Content (%)	<2.0%	Bulk Volume (L/kg)	

Applications

Plastics		Coatings		Inks		Other	
PVC	<input checked="" type="checkbox"/>	Decorative	<input checked="" type="checkbox"/>	Water Flexo	<input type="checkbox"/>	Paper	
PE	<input checked="" type="checkbox"/>	Automotive/Aerospace	<input checked="" type="checkbox"/>	Solvent Flexo	<input type="checkbox"/>	Rubber	
PP	<input checked="" type="checkbox"/>	Industrial	<input checked="" type="checkbox"/>	InkJet	<input type="checkbox"/>	Finger Paints	
PS	<input type="checkbox"/>	Powder	<input checked="" type="checkbox"/>	UV	<input type="checkbox"/>	Seed Coatings	
PET	<input type="checkbox"/>			Offset	<input type="checkbox"/>		
Fiber	<input type="checkbox"/>						

Not Frequently Used Limited Recommended

Comments:

DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL: The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production.