



DCC Red 7254

Description: DCC Red 7254 is a high performance mid shade red pigment for use in high-end coatings and plastic applications where excellent fastness properties are required. FDA Approved.

Chemical Type	Diketopyrrolopyrrole Red	Constitution No.	56110
Color Index	Pigment Red 254	CAS No.	84632-65-5

Resistance Properties

MEK	5	Ethanol	5
Water	5	Ethyl Acetate	5
Mineral Spirits	5	Acid	5
Xylene	5	Alkali	5

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Product Characteristics

Migration (1-5)		Lightfastness (1-8): Masstone	8
Heat Stability (°C/°F)	200°C (Paints) 300°C (HDPE)	Lightfastness (1-8): Tint 1:10	8
Warpage Rating (1-3) * Plastic Only	3	Weatherfastness (1-5): Masstone	5
Overpaint Resistance * Paints Only		Weatherfastness (1-5): Tint 1:10	5

Warpage: 1 = minimal, 2 = some, 3 = severe Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=Very Good, 8=Excellent

Physical Properties

Particle Size (µm)		pH	5.5-8.5
Specific Surface Area (m²/g)		Specific Gravity	1.6
Oil Absorption (g/100g)	41	Bulk Density (kg/L)	
Moisture Content (%)	<1.0%	Bulk Volume (L/kg)	

Applications

Plastics	Coatings	Inks	Other
PVC <input checked="" type="checkbox"/>	Decorative <input checked="" type="checkbox"/>	Water Flexo <input checked="" type="checkbox"/>	Paper
PE <input checked="" type="checkbox"/>	Automotive/Aerospace <input checked="" type="checkbox"/>	Solvent Flexo <input type="checkbox"/>	Rubber
PP <input checked="" type="checkbox"/>	Industrial <input checked="" type="checkbox"/>	InkJet <input type="checkbox"/>	Finger Paints
PS <input checked="" type="checkbox"/>	Powder <input checked="" type="checkbox"/>	UV <input type="checkbox"/>	Seed Coatings
PET <input type="checkbox"/>		Offset <input checked="" type="checkbox"/>	
Fiber <input type="checkbox"/>			

Not Frequently Used Limited Recommended

Comments:

DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL: The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production.