



# DCC Yellow 1202

**Description:** DCC Yellow 1202 is a green shade semi-opaque yellow pigment used primarily in ink applications with minimal usage in coatings and plastics.

<b>Chemical Type</b>	Diarylide Yellow	<b>Constitution No.</b>	21095
<b>Color Index</b>	Pigment Yellow 14	<b>CAS No.</b>	5468-75-7

## Resistance Properties

<b>MEK</b>	5	<b>Ethanol</b>	5
<b>Water</b>	5	<b>Ethyl Acetate</b>	3
<b>Mineral Spirits</b>	5	<b>Acid</b>	5
<b>Xylene</b>	5	<b>Alkali</b>	4

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

## Product Characteristics

<b>Migration (1-5)</b>		<b>Lightfastness (1-8): Masstone</b>	6
<b>Heat Stability (°C/°F)</b>	180°C (Paints) 200°C (HDPE)	<b>Lightfastness (1-8): Tint 1:10</b>	5
<b>Warpage Rating (1-3) * Plastic Only</b>		<b>Weatherfastness (1-5): Masstone</b>	2
<b>Overpaint Resistance * Paints Only</b>		<b>Weatherfastness (1-5): Tint 1:10</b>	1

Warpage: 1 = minimal, 2 = some, 3 = severe    Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent    Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=Very Good, 8=Excellent

## Physical Properties

<b>Particle Size (µm)</b>		<b>pH</b>	5.5-8.5
<b>Specific Surface Area (m<sup>2</sup>/g)</b>		<b>Specific Gravity</b>	1.4
<b>Oil Absorption (g/100g)</b>	29	<b>Bulk Density (kg/L)</b>	
<b>Moisture Content (%)</b>	<2.0%	<b>Bulk Volume (L/kg)</b>	

## Applications

Plastics		Coatings		Inks		Other	
PVC	<input type="checkbox"/>	Decorative	<input type="checkbox"/>	Water Flexo	<input checked="" type="checkbox"/>	Paper	
PE	<input type="checkbox"/>	Automotive/Aerospace	<input type="checkbox"/>	Solvent Flexo	<input checked="" type="checkbox"/>	Rubber	
PP	<input type="checkbox"/>	Industrial	<input checked="" type="checkbox"/>	InkJet	<input type="checkbox"/>	Finger Paints	
PS	<input type="checkbox"/>	Powder	<input checked="" type="checkbox"/>	UV	<input type="checkbox"/>	Seed Coatings	
PET	<input type="checkbox"/>			Offset	<input checked="" type="checkbox"/>		
Fiber	<input type="checkbox"/>						

Not Frequently Used     Limited     Recommended

**Comments:** At temperatures >200°C, when incorporated in polymers, the pigment may decompose to form measurable amounts of DCB, which is a suspect human carcinogen

**DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL:** The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production.