



DCC Yellow 1364

Description: DCC Yellow 1364 is a medium to red shade yellow pigment for use in various plastics applications. DCC Yellow 1364 can be used as a heavy metal free alternate to PY.34

Chemical Type	Monoazo	Constitution No.	13940
Color Index	Pigment Yellow 62	CAS No.	12286-66-7

Resistance Properties

MEK	3	Ethanol	4
Water	4	Ethyl Acetate	3
Mineral Spirits	4	Acid	3
Xylene	3	Alkali	3

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Product Characteristics

Migration (1-5)	5	Lightfastness (1-8): Masstone	7
Heat Stability (°C/°F)	240°C (HDPE)	Lightfastness (1-8): Tint 1:10	4
Warpage Rating (1-3) * Plastic Only	2	Weatherfastness (1-5): Masstone	5
Overpaint Resistance * Paints Only		Weatherfastness (1-5): Tint 1:10	1

Warpage: 1 = minimal, 2 = some, 3 = severe Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=Very Good, 8=Excellent

Physical Properties

Particle Size (µm)		pH	5.5-8.5
Specific Surface Area (m²/g)		Specific Gravity	1.5
Oil Absorption (g/100g)	44	Bulk Density (kg/L)	
Moisture Content (%)	<2.0%	Bulk Volume (L/kg)	

Applications

Plastics		Coatings		Inks		Other	
PVC	■	Decorative	<input type="checkbox"/>	Water Flexo	<input type="checkbox"/>	Paper	
PE	■	Automotive/Aerospace	<input type="checkbox"/>	Solvent Flexo	<input type="checkbox"/>	Rubber	■
PP	■	Industrial	<input type="checkbox"/>	InkJet	<input type="checkbox"/>	Finger Paints	
PS	■	Powder	<input type="checkbox"/>	UV	<input type="checkbox"/>	Seed Coatings	
PET	<input type="checkbox"/>			Offset	<input type="checkbox"/>		
Fiber	<input type="checkbox"/>						

Not Frequently Used Limited Recommended

Comments:

DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL: The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production.