



# GemSpense Black GX7/V2

**Description:** Surfactant and Water Based Dispersion of Carbon Black

<b>Chemical Type</b>	Carbon Black	<b>Constitution No.</b>	77266
<b>Color Index</b>	Pigment Black 7	<b>CAS No.</b>	1333-86-4

## Resistance Properties

<b>MEK</b>	5	<b>Ethanol</b>	5
<b>Water</b>	5	<b>Ethyl Acetate</b>	5
<b>Mineral Spirits</b>	5	<b>Acid</b>	5
<b>Xylene</b>	5	<b>Alkali</b>	5

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

## Product Characteristics

<b>Heat Stability (°C/°F)</b>	300°C	<b>Weatherfastness (1-5): Masstone</b>
<b>Lightfastness (1-8): Masstone</b>	8	<b>Weatherfastness (1-5): Tint 1:10</b>
<b>Lightfastness (1-8): Tint 1:10</b>	8	

Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=VG, 8=Excellent

## Physical Properties

<b>Fineness of Grind (µm)</b>	<10	<b>Specific Gravity</b>	1 - 1.3
<b>Volatile Organic Content (ppm)</b>		<b>Viscosity (cP)</b>	4500 - 5000
<b>pH</b>	6 - 8	<b>Pigment Content (%)</b>	40

## Applications

Plastics		Coatings		Inks		Other	
PVC	<input type="checkbox"/>	Decorative	<input checked="" type="checkbox"/>	Water Flexo	<input type="checkbox"/>	Paper	<input type="checkbox"/>
PE	<input type="checkbox"/>	Automotive/Aerospace	<input checked="" type="checkbox"/>	Solvent Flexo	<input type="checkbox"/>	Rubber Latex	<input checked="" type="checkbox"/>
PP	<input type="checkbox"/>	Industrial	<input checked="" type="checkbox"/>	InkJet	<input type="checkbox"/>	Finger Paints	<input checked="" type="checkbox"/>
PS	<input type="checkbox"/>	Powder	<input type="checkbox"/>	UV	<input checked="" type="checkbox"/>	Seed Coatings	<input checked="" type="checkbox"/>
PET	<input type="checkbox"/>			Offset	<input checked="" type="checkbox"/>		

Not Frequently Used     Limited     Recommended

**Comments:** Carbon black. Several grades used, but all have very high color strength. Specific grades give high jetness, good conductivity and preferred physiological properties. All have excellent fastness properties.

**DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL:** The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production. Shelf life for GemSpense products is 1 year.