



See The Difference We Make

GemSperse Blue EX29

Description: Surfactant and Water Based Dispersion of Ultramarine Blue 29

Chemical Type	Ultramarine Blue	Constitution No.	77007
Color Index	Pigment Blue 29	CAS No.	57455-37-5

Resistance Properties

MEK	5	Ethanol	5
Water	4	Ethyl Acetate	5
Mineral Spirits	5	Acid	1
Xylene	5	Alkali	4

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Product Characteristics

Heat Stability (°C/°F)	300°C	Weatherfastness (1-5): Masstone
Lightfastness (1-8): Masstone	8	Weatherfastness (1-5): Tint 1:10
Lightfastness (1-8): Tint 1:10	8	

Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=VG, 8=Excellent

Physical Properties

Fineness of Grind (µm)	<10	Specific Gravity	1.3 - 1.5
Volatile Organic Content (ppm)	<700	Viscosity (cP)	1000 - 3000
pH	8.5 - 9.5	Pigment Content (%)	50

Applications

Plastics		Coatings		Inks		Other	
PVC	○	Decorative	●	Water Flexo	○	Paper	○
PE	○	Automotive/Aerospace	○	Solvent Flexo	○	Rubber Latex	●
PP	○	Industrial	●	InkJet	○	Finger Paints	○
PS	○	Powder	○	UV	○	Seed Coatings	●
PET	○			Offset	○		

○ Not Frequently Used ○ Limited ● Recommended

Comments: Ultramarine. Very pure reddish blue with low color strength but good fastness properties, except to acids. Relatively cheap and useful for applications which are required to be copper-free.

DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL: The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production. Shelf life for all GemSperse products is 1 year.