



See The Difference We Make

GemSperse Green KX7

Description: Anionic Water Based Dispersion of Phthalocyanine Green

Chemical Type	Phthalocyanine Green	Constitution No.	74260
Color Index	Pigment Green 7	CAS No.	1328-53-6

Resistance Properties

MEK	5	Ethanol	5
Water	5	Ethyl Acetate	5
Mineral Spirits	5	Acid	5
Xylene	5	Alkali	5

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Product Characteristics

Heat Stability (°C/°F)	300°C	Weatherfastness (1-5): Masstone
Lightfastness (1-8): Masstone	8	Weatherfastness (1-5): Tint 1:10
Lightfastness (1-8): Tint 1:10	8	

Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=VG, 8=Excellent

Physical Properties

Fineness of Grind (µm)	<10	Specific Gravity	1.3 - 1.5
Volatile Organic Content (ppm)		Viscosity (cP)	500 - 2000
pH	8 - 9.5	Pigment Content (%)	40

Applications

Plastics	Coatings	Inks	Other
PVC	Decorative	Water Flexo	Paper
PE	Automotive/Aerospace	Solvent Flexo	Rubber Latex
PP	Industrial	InkJet	Finger Paints
PS	Powder	UV	Seed Coatings
PET		Offset	

○ Not Frequently Used ○ Limited ● Recommended

Comments: Strong blue green with excellent fastness to light, solvents and heat. Used for all applications. Economic.

DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL: The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production. Shelf life for GemSperse products is 1 year.