



# GemSperser Red BA101 BS

**Description:** Surfactant and Water Based Dispersion of Opaque Red 101 (Blue Shade)

<b>Chemical Type</b>	Opaque Red Iron Oxide	<b>Constitution No.</b>	77491
<b>Color Index</b>	Pigment Red 101	<b>CAS No.</b>	1309-37-1

## Resistance Properties

<b>MEK</b>	5	<b>Ethanol</b>	5
<b>Water</b>	5	<b>Ethyl Acetate</b>	5
<b>Mineral Spirits</b>	5	<b>Acid</b>	4
<b>Xylene</b>	5	<b>Alkali</b>	4

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

## Product Characteristics

<b>Heat Stability (°C/°F)</b>	200°C	<b>Weatherfastness (1-5): Masstone</b>
<b>Lightfastness (1-8): Masstone</b>	8	<b>Weatherfastness (1-5): Tint 1:10</b>
<b>Lightfastness (1-8): Tint 1:10</b>	8	

Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=VG, 8=Excellent

## Physical Properties

<b>Fineness of Grind (µm)</b>	<10	<b>Specific Gravity</b>	1.7 - 2.1
<b>Volatile Organic Content (ppm)</b>	<700	<b>Viscosity (cP)</b>	1000 - 3000
<b>pH</b>	8 - 9.5	<b>Pigment Content (%)</b>	70

## Applications

Plastics		Coatings		Inks		Other	
PVC	<input type="checkbox"/>	Decorative	<input checked="" type="checkbox"/>	Water Flexo	<input checked="" type="checkbox"/>	Paper	<input type="checkbox"/>
PE	<input type="checkbox"/>	Automotive/Aerospace	<input checked="" type="checkbox"/>	Solvent Flexo	<input type="checkbox"/>	Rubber Latex	<input checked="" type="checkbox"/>
PP	<input type="checkbox"/>	Industrial	<input checked="" type="checkbox"/>	InkJet	<input type="checkbox"/>	Finger Paints	<input type="checkbox"/>
PS	<input type="checkbox"/>	Powder	<input type="checkbox"/>	UV	<input checked="" type="checkbox"/>	Seed Coatings	<input checked="" type="checkbox"/>
PET	<input type="checkbox"/>			Offset	<input checked="" type="checkbox"/>		

Not Frequently Used     Limited     Recommended

**Comments:** Ferric Oxide (Fe<sub>2</sub>O<sub>3</sub>). Wide range of shades but mostly in the dull red ochre color with low tinting strength. Otherwise ideal application properties with excellent fastness to light, solvents and chemicals and a relatively low price. Normally opaque - some transparent grades are much more expensive but widely used for transparent wood finishes. Good physiological properties

**DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL:** The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production. Shelf life for GemSperser products is 1 year.