



See The Difference We Make

GemSperser Red EX101 BS

Description: Surfactant and Water Based Dispersion of Opaque Red 101

Chemical Type	Opaque Red Iron Oxide	Constitution No.	77491
Color Index	Pigment Red 101	CAS No.	1309-37-1

Resistance Properties

MEK	5	Ethanol	5
Water	5	Ethyl Acetate	5
Mineral Spirits	5	Acid	4
Xylene	5	Alkali	4

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Product Characteristics

Heat Stability (°C/°F)	200°C	Weatherfastness (1-5): Masstone
Lightfastness (1-8): Masstone	8	Weatherfastness (1-5): Tint 1:10
Lightfastness (1-8): Tint 1:10	8	

Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=VG, 8=Excellent

Physical Properties

Fineness of Grind (µm)	<10	Specific Gravity	1.8 - 2.1
Volatile Organic Content (ppm)	<700	Viscosity (cP)	2500 - 3500
pH	8 - 9.5	Pigment Content (%)	70

Applications

Plastics		Coatings		Inks		Other	
PVC	<input type="checkbox"/>	Decorative	<input checked="" type="checkbox"/>	Water Flexo	<input checked="" type="checkbox"/>	Paper	<input type="checkbox"/>
PE	<input type="checkbox"/>	Automotive/Aerospace	<input checked="" type="checkbox"/>	Solvent Flexo	<input type="checkbox"/>	Rubber Latex	<input checked="" type="checkbox"/>
PP	<input type="checkbox"/>	Industrial	<input checked="" type="checkbox"/>	InkJet	<input type="checkbox"/>	Finger Paints	<input type="checkbox"/>
PS	<input type="checkbox"/>	Powder	<input type="checkbox"/>	UV	<input checked="" type="checkbox"/>	Seed Coatings	<input checked="" type="checkbox"/>
PET	<input type="checkbox"/>			Offset	<input checked="" type="checkbox"/>		

Not Frequently Used Limited Recommended

Comments: A wide range of dull red shades with low tinting strength, but excellent fastness to light, solvents and chemicals and a relatively low price. Normally opaque. Transparent grades are more expensive and mainly used for transparent wood finishes.

DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL: The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production. Shelf life for GemSperser products is 1 year.