



See The Difference We Make

GemSperse Red EX170 BS

Description: Surfactant and Water Based Dispersion of Red 170

Chemical Type	Monoazo Red	Constitution No.	12475
Color Index	Pigment Red 170	CAS No.	2786-76-7

Resistance Properties

MEK	4	Ethanol	4
Water	5	Ethyl Acetate	4
Mineral Spirits	5	Acid	5
Xylene	4	Alkali	5

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Product Characteristics

Heat Stability (°C/°F)	160°C	Weatherfastness (1-5): Masstone	3D
Lightfastness (1-8): Masstone	6	Weatherfastness (1-5): Tint 1:10	2
Lightfastness (1-8): Tint 1:10	4-5		

Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=VG, 8=Excellent

Physical Properties

Fineness of Grind (µm)	<10	Specific Gravity	1 - 1.2
Volatile Organic Content (ppm)	<700	Viscosity (cP)	1000 - 3000
pH	8 - 9.5	Pigment Content (%)	40

Applications

Plastics	Coatings	Inks	Other
PVC <input type="checkbox"/>	Decorative <input checked="" type="checkbox"/>	Water Flexo <input checked="" type="checkbox"/>	Paper <input type="checkbox"/>
PE <input type="checkbox"/>	Automotive/Aerospace <input checked="" type="checkbox"/>	Solvent Flexo <input type="checkbox"/>	Rubber Latex <input checked="" type="checkbox"/>
PP <input type="checkbox"/>	Industrial <input checked="" type="checkbox"/>	InkJet <input checked="" type="checkbox"/>	Finger Paints <input type="checkbox"/>
PS <input type="checkbox"/>	Powder <input type="checkbox"/>	UV <input checked="" type="checkbox"/>	Seed Coatings <input checked="" type="checkbox"/>
PET <input type="checkbox"/>		Offset <input checked="" type="checkbox"/>	

Not Frequently Used Limited Recommended

Comments: A bright mid red with good fastness to light, good heat stability and very good solvent fastness. Used for industrial paints and textiles.

DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL: The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production. Shelf life for GemSperse products is 1 year.