



# GemSperse Magenta GX122

**Description:** Surfactant and Water Based Dispersion of Red 122

<b>Chemical Type</b>	Quinacridone Red	<b>Constitution No.</b>	73915
<b>Color Index</b>	Pigment Red 122	<b>CAS No.</b>	980-26-7

## Resistance Properties

<b>MEK</b>	4	<b>Ethanol</b>	4
<b>Water</b>	4	<b>Ethyl Acetate</b>	5
<b>Mineral Spirits</b>	5	<b>Acid</b>	5
<b>Xylene</b>	5	<b>Alkali</b>	5

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

## Product Characteristics

<b>Heat Stability (°C/°F)</b>	200°C	<b>Weatherfastness (1-5): Masstone</b>
<b>Lightfastness (1-8): Masstone</b>	8	<b>Weatherfastness (1-5): Tint 1:10</b>
<b>Lightfastness (1-8): Tint 1:10</b>	8	

Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=VG, 8=Excellent

## Physical Properties

<b>Fineness of Grind (µm)</b>	<10	<b>Specific Gravity</b>	1 - 1.2
<b>Volatile Organic Content (ppm)</b>		<b>Viscosity (cP)</b>	1000 - 2500
<b>pH</b>	8 - 9.5	<b>Pigment Content (%)</b>	26

## Applications

Plastics		Coatings		Inks		Other	
PVC	<input type="checkbox"/>	Decorative	<input checked="" type="checkbox"/>	Water Flexo	<input type="checkbox"/>	Paper	<input type="checkbox"/>
PE	<input type="checkbox"/>	Automotive/Aerospace	<input checked="" type="checkbox"/>	Solvent Flexo	<input type="checkbox"/>	Rubber Latex	<input checked="" type="checkbox"/>
PP	<input type="checkbox"/>	Industrial	<input checked="" type="checkbox"/>	InkJet	<input type="checkbox"/>	Finger Paints	<input checked="" type="checkbox"/>
PS	<input type="checkbox"/>	Powder	<input type="checkbox"/>	UV	<input checked="" type="checkbox"/>	Seed Coatings	<input checked="" type="checkbox"/>
PET	<input type="checkbox"/>			Offset	<input checked="" type="checkbox"/>		

Not Frequently Used     Limited     Recommended

**Comments:** A brilliant magenta shade with excellent fastness to light, heat and solvents. Used for top quality applications.

**DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL:** The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production. Shelf life for GemSperse products is 1 year.