



See The Difference We Make

GemSperse White EX6

Description: Surfactant and Water Based Dispersion of Titanium Dioxide

Chemical Type	Titanium Dioxide	Constitution No.	77891
Color Index	Pigment White 6	CAS No.	13463-67-7

Resistance Properties

MEK	5	Ethanol	5
Water	5	Ethyl Acetate	5
Mineral Spirits	5	Acid	5
Xylene	5	Alkali	5

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Product Characteristics

Heat Stability (°C/°F)	200°C	Weatherfastness (1-5): Masstone
Lightfastness (1-8): Masstone	8	Weatherfastness (1-5): Tint 1:10
Lightfastness (1-8): Tint 1:10	-	

Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=VG, 8=Excellent

Physical Properties

Fineness of Grind (µm)	<10	Specific Gravity	1.8 - 2
Volatile Organic Content (ppm)	<700	Viscosity (cP)	1000 - 3000
pH	8 - 9.5	Pigment Content (%)	65

Applications

Plastics	Coatings	Inks	Other
PVC <input type="checkbox"/>	Decorative <input checked="" type="checkbox"/>	Water Flexo <input checked="" type="checkbox"/>	Paper <input type="checkbox"/>
PE <input type="checkbox"/>	Automotive/Aerospace <input checked="" type="checkbox"/>	Solvent Flexo <input type="checkbox"/>	Rubber Latex <input checked="" type="checkbox"/>
PP <input type="checkbox"/>	Industrial <input checked="" type="checkbox"/>	InkJet <input checked="" type="checkbox"/>	Finger Paints <input type="checkbox"/>
PS <input type="checkbox"/>	Powder <input type="checkbox"/>	UV <input type="checkbox"/>	Seed Coatings <input checked="" type="checkbox"/>
PET <input type="checkbox"/>		Offset <input checked="" type="checkbox"/>	

Not Frequently Used Limited Recommended

Comments: Titanium Dioxide - TiO2 (Rutile form). Good color with very high covering power. Good chemical and physiological properties. Excellent heat stability and fastness properties.

DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL: The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production. Shelf life for GemSperse products is 1 year.