



# 8916 Transparent Yellow Iron Oxide

Lanox Iron Oxide

**Description:** 8916 is a high performance transparent yellow iron oxide offering high color strength, weather resistance and UV protection properties.

<b>Chemical Type</b>	Syn Yellow Iron Oxide	<b>Constitution No.</b>	77492
<b>Color Index</b>	Pigment Yellow 42	<b>CAS No.</b>	51274-00-1

## Typical Chemical and Physical Properties

<b>Fe Content (Fe<sub>2</sub>O<sub>3</sub>) - % Min.</b>	82
<b>Volatile Matter (220°F) - % Max.</b>	3.0
<b>pH</b>	5.0 - 8.0
<b>Water Soluble Salts (% Max.)</b>	0.3
<b>Oil Absorption (g/100g)</b>	30 - 40
<b>Sieve Residue (325 mesh) - % Max.</b>	0.05
<b>UV absorption (%)</b>	≥95
<b>Heat Stability</b>	171°C (HDPE)
<b>Weatherfastness</b>	5
<b>Lightfastness</b>	8

Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent    Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=Very Good, 8=Excellent

## Applications

Plastics	Coatings	Inks	Other
PVC <input checked="" type="checkbox"/>	Decorative	Water Flexo	Paper
PE	Automotive/Aerospace <input checked="" type="checkbox"/>	Solvent Flexo <input checked="" type="checkbox"/>	Rubber
PP	Industrial <input checked="" type="checkbox"/>	InkJet	Finger Paints
PS	Powder <input checked="" type="checkbox"/>	UV	Seed Coatings
PET		Offset	
Fiber			

Not Frequently Used     Limited     Recommended

**Comments:** 8916 is primarily recommended for wood coatings.

**DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL:** The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production.