



# PR-258 Barium Lithol Red 49:1

**Description:** PR-258 is a transparent blue shade red pigment with low viscosity and excellent tinting strength

<b>Chemical Type</b>	Barium Lithol Red	<b>Constitution No.</b>	15630:1
<b>Color Index</b>	Pigment Red 49:1	<b>CAS No.</b>	1103-38-4

## Resistance Properties

<b>MEK</b>	4	<b>Ethanol</b>	3
<b>Water</b>	4 - 5	<b>Ethyl Acetate</b>	3 - 4
<b>Mineral Spirits</b>	4 - 5	<b>Acid</b>	4 - 5
<b>Xylene</b>	4	<b>Alkali</b>	1 - 2

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

## Product Characteristics

<b>Migration (1-5)</b>		<b>Lightfastness (1-8): Masstone</b>	3 - 4
<b>Heat Stability (°C/°F)</b>	127°C (Paints) 127°C (Inks)	<b>Lightfastness (1-8): Tint 1:10</b>	2
<b>Warpage Rating (1-3) * Plastic Only</b>		<b>Weatherfastness (1-5): Masstone</b>	
<b>Overpaint Resistance * Paints Only</b>		<b>Weatherfastness (1-5): Tint 1:10</b>	

Warpage: 1 = minimal, 2 = some, 3 = severe    Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent    Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=Very Good, 8=Excellent

## Physical Properties

<b>Particle Size (µm)</b>		<b>pH</b>	5.5 - 7.5
<b>Specific Surface Area (m²/g)</b>		<b>Specific Gravity</b>	1.5
<b>Oil Absorption (g/100g)</b>	45 - 55	<b>Bulk Density (kg/L)</b>	
<b>Moisture Content (%)</b>	4 - 6%	<b>Bulk Volume (L/kg)</b>	

## Applications

Plastics		Coatings		Inks		Other	
PVC	<input type="checkbox"/>	Decorative	<input type="checkbox"/>	Water Flexo	<input checked="" type="checkbox"/>	Paper	
PE	<input type="checkbox"/>	Automotive/Aerospace	<input type="checkbox"/>	Solvent Flexo	<input type="checkbox"/>	Rubber	
PP	<input type="checkbox"/>	Industrial	<input checked="" type="checkbox"/>	InkJet	<input type="checkbox"/>	Finger Paints	
PS	<input type="checkbox"/>	Powder	<input type="checkbox"/>	UV	<input type="checkbox"/>	Seed Coatings	
PET	<input type="checkbox"/>			Offset	<input checked="" type="checkbox"/>		
Fiber	<input type="checkbox"/>						

Not Frequently Used     Limited     Recommended

### Comments:

**DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL:** The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production.