DCL-1338 Pyrazolone Red, PR.38

Description: DCL-1338 is a very strong, yellow shade red diarylide pigment with good lightfastness.

Chemical Type	Pyrazolone Red	**Constitution No.**	21120
Color Index	Pigment Red 38	**CAS No.**	6358-87-8

Resistance Properties

MEK	3	**Ethanol**	4
Water	5	**Ethyl Acetate**	
Mineral Spirits	5	**Acid**	5
Xylene	2	**Alkali**	5

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent

Product Characteristics

Migration (1-5)		**Lightfastness (1-8): Masstone**	6 - 7
Heat Stability (°C/°F)	200°C (HDPE)	**Lightfastness (1-8): Tint 1:10**	6
Warpage Rating (1-3) * Plastic Only		**Weatherfastness (1-5): Masstone**	
Overpaint Resistance * Paints Only		**Weatherfastness (1-5): Tint 1:10**	

Warpage: 1 = minimal, 2 = some, 3 = severe Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=Very Good, 8=Excellent

Physical Properties

Particle Size (µm)		**pH**	5.0 - 7.0
Specific Surface Area (m^2/g)		**Specific Gravity**	1.4
Oil Absorption (g/100g)		**Bulk Density (kg/L)**	
Moisture Content (%)	≤ 2.0%	**Bulk Volume (L/kg)**	

Applications

Plastics		Coatings		Inks		Other	
PVC	■	**Decorative**	☐	**Water Flexo**	■	**Paper**	
PE	■	**Automotive/Aerospace**	☐	**Solvent Flexo**	☐	**Rubber**	■
PP	☐	**Industrial**	☐	**InkJet**	☐	**Finger Paints**	
PS	☐	**Powder**	☐	**UV**	☐	**Seed Coatings**	
PET	☐			**Offset**	☐		
Fiber	☐						

☐ Not Frequently Used ◘ Limited ■ Recommended

Comments: At temperatures >200°C, when incoporated in polmyers, the pigment may decompose to form measurable amounts of DCB, which is a suspect human carcinogen.

DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL: The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production.

Version 2. July 2022