DCL-8140M Syn Micronized Red Iron Oxide, PR.101

Lanox Iron Oxide

Description: DCL-8140M is a micronized synthetic red iron oxide. DCL-8140M is bluer than DCL-8130BM. DCL-8140M is FDA approved (Section 178.3297).

Chemical Type	Syn Micronized Red Iron Oxide	**Constitution No.**	77491
Color Index	Pigment Red 101	**CAS No.**	1309-37-1

Typical Chemical and Physical Properties

Fe Content (Fe_2O_3) - % Min.	96
Volatile Matter (220°F) - % Max.	0.50
pH	4.5 – 7.5
Particle Shape	Spherical
Water Soluble Salts (% Max.)	0.60
Oil Absorption (g/100g)	15 - 25
Sieve Residue (325 mesh) - % Max.	0.008
Tamped Apparent Density (g/cm^3)	0.70 – 1.00
Density (g/cm^3)	5.0
Heat Stability	504°C (HDPE)
Moisture Content (%)	<1.0
Weatherfastness	5
Lightfastness	8

Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=Very Good, 8=Excellent

Applications

Plastics		Coatings		Inks	Other
PVC	■	**Decorative**	■	**Water Flexo**	**Paper**
PE	■	**Automotive/Aerospace**		**Solvent Flexo**	**Rubber**
PP	■	**Industrial**	■	**InkJet**	**Finger Paints**
PS	■	**Powder**	■	**UV**	**Seed Coatings**
PET	■			**Offset**	
Fiber					

☐ Not Frequently Used ◘ Limited ■ Recommended

Comments:

DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL: The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production.