# DCL Quindo® Magenta 122 2286832

**Description:** This is a soft textured Quinacridone magenta pigment toner. It has a clean magenta undertone and high tinctorial strength. This pigment is recommended for industrial applications.

| | | | |
|---|---|---|---|
| **Chemical Type** | Quinacridone | **Constitution No.** | 73915 |
| **Color Index** | Pigment Red 122 | **CAS No.** | 980-26-7 |

## Resistance Properties

| | | | |
|---|---|---|---|
| **MEK** | 4-5 | **Ethanol** | 4 |
| **Water** | 5 | **Ethyl Acetate** | 4 |
| **Mineral Spirits** | 5 | **Acid** | 4-5 |
| **Xylene** | 5 | **Alkali** | 4 |

Legend: 1=Poor, 2=Fair, 3=Good, 4=Very good, 5=Excellent

## Product Characteristics

| | | | |
|---|---|---|---|
| **Migration (1-5)** | | **Lightfastness (1-8): Masstone** | 7-8 |
| **Heat Stability (°C/°F)** | 200°C (Paint) | **Lightfastness (1-8): Tint 1:10** | 7 |
| **Warpage Rating (1-3) * Plastic Only** | | **Weatherfastness (1-5): Masstone** | 4-5 |
| **Overpaint Resistance * Paints Only** | 5 | **Weatherfastness (1-5): Tint 1:10** | 4 |

Warpage: 1 = minimal, 2 = some, 3 = severe  Weatherfastness: 1=Poor, 2=Fair, 3=Good, 4=Very Good, 5=Excellent  Lightfastness: 1-2=Poor, 3-4=Fair, 5=Good, 6-7=Very Good, 8=Excellent

## Physical Properties

| | | | |
|---|---|---|---|
| **Particle Size (µm)** | | **pH** | 5.5 - 8.5 |
| **Specific Surface Area ($m^2/g$)** | 82 | **Specific Gravity** | 1.42 |
| **Oil Absorption (g/100g)** | 56 | **Bulk Density (kg/L)** | |
| **Moisture Content (%)** | <2.0 | **Bulk Volume (L/kg)** | |

## Applications

| Plastics | | Coatings | | Inks | | Other |
|---|---|---|---|---|---|---|
| **PVC** | ☐ | **Decorative** | ■ | **Water Flexo** | ☐ | **Paper** |
| **PE** | ☐ | **Automotive/Aerospace** | ■ | **Solvent Flexo** | ☐ | **Rubber** |
| **PP** | ☐ | **Industrial** | ■ | **InkJet** | ☐ | **Finger Paints** |
| **PS** | ☐ | **Powder** | ◘ | **UV** | ☐ | **Seed Coatings** |
| **PET** | ☐ | **Coil** | ◘ | **Offset** | ☐ | |
| **Fiber** | ☐ | | | | | |

☐ Not Frequently Used  Limited  ■ Recommended

**Comments:**

**DISCLAIMER OF LIABILITY FOR RELIANCE ON INFORMATION PROVIDED BY DCL:** The information contained herein is true and accurate to the best of our knowledge and are deemed as typical values, being therefore provided without warranty or guarantee. Since the conditions of use are beyond our control, DCL disclaims all liability and assumes no legal responsibility for damages resulting from use of or reliance upon the information contained herein. DCL strongly recommends careful screening/testing before using its products in production.